



Stamford Products Limited
Bayley Street, Stalybridge
Cheshire SK15 1QQ
Telephone: 0161-330 5570 Telefax: 0161-330 5576
Email: enquiry@micropol.co.uk
Web site: www.micropol.co.uk

TECHNICAL DATA SHEET

ISOPLAS P651

MECHANICAL

PHYSICAL PROPERTY	TEST METHOD	UNITS	VALUE
Density	ISO 1183	g/cm ³	0.960
Tensile Strength at Yield	ASTM D638	MPa	31.0
Elongation at Break	ASTM D638	%	70
Modulus of Elasticity	ASTM D638	MPa	1800

THERMAL

PHYSICAL PROPERTY	TEST METHOD	UNITS	VALUE
Melt Flow Index (190/5)	ISO 1133	g/10 min	1.5
Vicat Softening Point	ASTM D1525	°C	130
Specific Heat	ISO 11357	kJ/kg.°C	2.1
Thermal Conductivity	ASTM D5930	W/m.°C	0.46
Coefficient of Linear Expansion (20°C)	ASTM D696	per °C	1.4 x 10 ⁻⁴

Isoplas P651 is used for rigid pipes for water transport, and for general purpose use.

The information given above is typical for the material. It should only be used for the purpose of comparison and does not guarantee performance under end use conditions.



SPL A member of The Stamford Group of Companies



Registered in England No. 1652293
Registered Office as above